



THERMOLIT MERCURE

15-1 & 15-2



- Thermoplastic
- Extrusion

Durable reflective thermoplastic road marking with high visibility.

Environment



Roads & Highways



Urban

Performances



High durability



Daytime visibility



Night visibility

ADVANTAGES

- High durability : certified at 2 million rollovers.
- Excellent retro-reflection for optimal guidance at night.
- Very high level of daytime visibility.

PERFORMANCES, CERTIFICATIONS AND CONSUMPTIONS

	15-1	15-2
Performances	P6 Q4 R4 S2	P6 Q4 R4 S2
Certifications	1RH1595S2	1RH1594S2
Product dosage	2010 g/m ²	2120 g/m ²
Drop-on dosage	280 g/m ²	260 g/m ²
Drop-on	SWARCOLUX 125 850 M T14	G600 125 AC07 POTTERS



Application



Extruded



Screed



Manual

CONDITIONS FOR USE

■ Application

Heat the meltable bags to 165 – 190°C to obtain a fluid paste before applying. Must be dropped-on immediately after application with drop-on beads.

• Support

Clean and dry hydrocarbon or bituminous pavements, new or old. It is recommended to apply a Thermolit Primer AF to old concrete or hydrocarbon substrates. Fresh concrete floors (< 1 year) should be sandblasted.

• Température limite du support

5°C < T < 45°C

• Hydrométrie maximale

80 %

• Diluant

If necessary, add max. 1% Thermolit thinner. Do not use other thinners.

■ Storage

Protected from sunlight and frost, the paint will keep for 12 months in its original packaging. The reference is the manufacturing date affixed to the packaging.



THERMOLIT MERCURE 15-1 & 15-2

PACKING

20 kg meltable bags

TECHNICAL CHARACTERISTICS

Couleur	White
Luminance	EN1871 class LF6 ($\beta > 0,80$) Qd > 160 mcd.m-2.lx-1 (class Q4)
Retroreflexion	RL > 200 mcd.m-2.lx-1 (class R4)
Skid resistance	SRT > 0,50 (class S2)
Lifespan	2.000.000 rollovers (class P6)
Density	approx. 1,9 g/cm ³
Viscosity	solid at 20°C, thick liquid at 175°C
Drying	approx. 1 minute
Flashpoint	< 230°C
Application	Self-propelled machine equipped with an extrusion shoe or screed

SAFETY- ENVIRONMENT

Product for professional use.

Soiled packaging, cleaning and rinsing products are waste to be treated according to current regulations.

Contact our sales department to consult the Safety Data Sheet.

VELUVINE B.V.

Ramshoorn 11
4824 AG Breda, Holland
Tel: 31 76 5421200
E-mail : sales@veluvine.nl
www.veluvine.nl



VERSION DISPONIBLE



NETHERLANDS



UK



FRANCE



SPAIN



GERMANY

August 2024

2/2