

ROCALINE RÉTRO

« Reflective prefabricated strip guaranteeing long-lasting marking including on paving or irregular supports, ideal for securing stop, give way areas, etc. »

ADVANTAGES

► USAGE

- Very good night and day visibility
- Good anti-skid
- Suitable for many road supports, including paving
- High-durability marking: strip composed of 4 kg/m² of cold-applied road marking compound.
- High resistance due to its fibreglass reinforcement

► EXPLOITATION

- Ready to be applied: glued via a strip of thermofusible bituminous adhesive
- No waste: does not need or use liquid glue, or cleaning diluent
- Quick and easy to apply using a gas torch
- Minimal inconvenience during construction work, thanks to immediate return to service

SOCIAL AND ENVIRONMENTAL BENEFITS

- WASTE REDUCTION
No hazardous waste during installation
- FRENCH MANUFACTURING
Made in the Île-de-France region

ROCALINE RÉTRO



TECHNICAL CHARACTERISTICS

- Prefabricated tape made of methacrylate resin reinforced with fibreglass
- Density: 1,95 kg/l
- Variants:
 - Tapes of different widths packaged in 6ml rolls
 - Numbers and letters
 - Words white against a dark background or vice versa (e.g.: Payment Required, Deliverie, etc.)
 - Arrows

Other variants: please contact us



IMPLEMENTATION

- The tape is applied using a gas burner and extended blacksmith's pliers
- New or old concrete, coated, paving supports, etc. Not suitable for porous supports such as self-locking tiles
- Apply to a clean, dry surface
- Surface temperature limits: $5^{\circ}\text{C} < T < 45^{\circ}\text{C}$
- Maximum humidity: 80 %
- Position the Bitufix at the location of the marking and heat it until it boils
- In the case of irregular supports such as paving: use 2 coats of Bitufix heating each layer
- Place the strip of Rocaline on the Bitufix whilst continuing to heat it to keep it boiling
- Do not heat the top side of the strip



SAFETY - STORAGE

- Product intended for professional use
- Storage: in a dry, well-ventilated place, sheltered from frost, sunlight and sources of heat
- Shelf life: 24 months from date of manufacture, unopened in the original packaging
- Consult the Safety Data Sheet at www.quickfds.fr



AXIMUM INDUSTRIE
5, rue du Quai de Débarquement - 76100 ROUEN - France
aximum.com