



VELU-MARK



- Paint
- Two-component

Two-component polyurethane paint, very durable, solvent-free and quick-drying. It is ideal for application in halls, production areas, car parks or even distribution centers (food and non-food).

Environment



Interior



Road & Highway

ADVANTAGES

- Velu-Mark is characterized by low dirt absorption, easy cleaning and high shine.
- High level of durability (twisting movement) with a single layer thanks to a unique technology.
- Quick drying to limit discomfort to users.
- Ecological paint, solvent-free, VOC-free and odorless.

PERFORMANCES, CERTIFICATIONS AND CONSUMPTIONS

Product rate **540 gr/m² for a thickness of 0,4 mm***

*i.e. an equivalence of 400 ml/m²

Application technique



Manual

CONDITIONS FOR USE

■ Application

Mix the hardener with the Velu-Mark base (color) until you obtain a perfectly homogeneous material. Apply the product evenly with a roller or brush. Velu-Mark paint has a self-leveling effect but if necessary it is possible to use a squeegee to even out the surface.

• Support

Clean and dry bituminous coatings. It is recommended to apply an EP Primer to old concrete supports. Fresh concrete supports (< 1 year) must be sanded.

• Ground temperature limits

The application temperature must be between 5°C and 40°C.
For applications outside these temperatures, contact Veluvine.

■ Storage

Protected from sunlight and frost, the paint will keep for 6 months in its original packaging. The reference is the manufacturing date affixed to the packaging.



VELU-MARK

PACKAGING

Velu-Mark

9.8 L sets in metal packaging consisting of:

- Velu-Mark base in 6.5 L bucket
- Velu-Mark hardener in 3.3 L bucket

4.5 L sets in metal packaging consisting of:

- Velu-Mark base in 3.3 L bucket
- Velu-Mark hardener in 1.2 L bucket

TECHNICAL CHARACTERISTICS

Colours	White and standard colors (RAL 1023, 3020, 5017, 6024, 7042, 7043, 9004). Other colors on request
Density	1,45 gr/cm ³ for Velu-Mark base 1,15 gr/cm ³ for Velu-Mark hardener
Potlife	20 - 30 minutes
Ash content	100%
Solid content	100% (mixed)
Recommended thickness	400 microns
Surface drying	45 minutes
Appearance	Smooth, very shiny
Mix ratio	3.3 L of Velu-Mark hardener for 6.5 L of Velu-Mark base
Curing time	Circulation is possible after approximately 2 hours at 20°C, complete hardening after 24-48 hours
Application	Manual with roller, brush or squeegee

SAFETY - ENVIRONMENT

Flammable product for professional use.

Soiled packaging, cleaning and rinsing products are waste to be treated according to current regulations.

Contact our sales department to consult the Safety Data Sheet.

VELUVINE B.V.

Ramshoorn 11

4824 AG Breda, Holland

Tel: 31 76 5421200 • Fax: +31 76 5420288

E-mail : info@veluvine.nl

www.veluvine.nl



AVAILABLE VERSION



NETHERLANDS



UK



FRANCE



SPAIN



GERMANY